Claims Listing

1-9. (canceled)

10. (currently amended) A composition comprising

an extruded blend of

a) an organic material which is susceptible to oxidative, thermal or light-induced degradation, and

b) at least one compound of the formula I



(I)

wherein

R_0 is  , -O-, -S-, -SO-, $-SO_2-$ or  ,

R_1 and R_2 are each independently $-(CF_2)_pF$, wherein p is 4 to 15,

R_3 and R_4 are each independently of the other hydrogen, a fluorine containing group, C_1-C_{12}alkyl,

phenyl or  ;

or R_3 and R_4, together with the carbon atom to which they are bonded, form a C_5-C_8-cycloalkylidene ring that is unsubstituted or substituted by from 1 to 3 C_1-C_4alkyl groups;R_5, R_6, R_7 and R_8 are each independently of the other hydrogen, C_1-C_{12}alkyl or C_3-C_{12}alkenyl,

X_1 and X_2 are each independently of the other a direct bond or C_1-C_{12}alkylene,
m is 1 to 10'000, and
n is 0 to 10'000; and

where the organic material is polyester, polyacrylate, polymethacrylate or polypropylene.

11. (canceled)

12. (canceled)

13. (original) A composition according to claim **10** wherein component (b) is present in an amount of from 0.1 to 20 %, based on the weight of component (a).

14. (original) A composition according to claim **10**, comprising in addition, besides components (a) and (b), further additives.

15. (original) A composition according to claim **14**, comprising as further additives phenolic antioxidants, light-stabilizers and/or processing stabilizers.

16. (currently amended) A process for reducing the surface energy of organic materials which comprises incorporating therein via extrusion a compound of the formula I



(I)

wherein

R_0 is  , -O-, -S-, -SO-, $-SO_2-$ or  ,

R_1 and R_2 are each independently $-(CF_2)_pF$, wherein p is 4 to 15,

R_3 and R_4 are each independently of the other hydrogen, a fluorine containing group, C_1-C_{12}alkyl,

phenyl or  ;

or R_3 and R_4, together with the carbon atom to which they are bonded, form a C_5-C_8-cycloalkylidene ring that is unsubstituted or substituted by from 1 to 3 C_1-C_4alkyl groups;R_5, R_6, R_7 and R_8 are each independently of the other hydrogen, C_1-C_{12}alkyl or C_3-C_{12}alkenyl,

X_1 and X_2 are each independently of the other a direct bond or C_1-C_{12}alkylene,

m is 1 to 10'000, and

n is 0 to 10'000; and

where the organic materials are polyester, polyacrylate, polymethacrylate or polypropylene.

17. (canceled)

18. (previously presented) A composition according to claim **10**, where in the compounds of formula I,

R_0 is  ,

R_3 and R_4 are each independently of the other hydrogen, CF_3, C_1-C_{12}alkyl, phenyl or



or R_3 and R_4, together with the carbon atom to which they are bonded, form a C_5-C_8-cycloalkylidene ring that is unsubstituted or substituted by from 1 to 3 C_1-C_4alkyl groups;

R_5, R_6, R_7 and R_8 are hydrogen,

X_1 and X_2 are each independently of the other C_1-C_{12}alkylene,

m is 1 to 10'000, and

n is 0 to 10'000.

19. (previously presented) A composition according to claim **10**, where in the compounds of formula I,

R_0 is  ,

R_3 is hydrogen, CF_3, C_1-C_{12}alkyl, phenyl or



R_4 is hydrogen, CF_3, C_1-C_{12}alkyl or phenyl;

or R_3 and R_4, together with the carbon atom to which they are bonded, form a C_5-C_8-cycloalkylidene ring that is unsubstituted or substituted by from 3 C_1-C_4alkyl groups;

R_5, R_6, R_7 and R_8 are hydrogen,

X_1 and X_2 are each independently of the other C_1-C_{12}alkylene,

m is 1 to 10'000, and

n is 0 to 10'000.

20. (previously presented) A composition according to claim **10**, where in the compounds of formula I,

R_0 is  and R_3 and R_4 are each independently of the other hydrogen or C_1-C_4alkyl or R_3 and R_4, together with the carbon atom to which they are bonded, form a cyclohexylidene ring.

21. (previously presented) A composition according to claim **10**, where in the compounds of formula I,

X_1 and X_2 are each independently of the other C_2-C_8alkylene.

22. (previously presented) A composition according to claim **10**, where in the compounds of formula I,

m is 1 to 50, and n is 0 to 50.

23. (previously presented) A composition according to claim **10**, where in the compounds of formula I,

R_0 is  ,

R_3 and R_4 are each independently of the other C_1-C_4alkyl;

or R_3 and R_4, together with the carbon atom to which they are bonded, form a cyclohexylidene ring;

R_5, R_6, R_7 and R_8 are hydrogen,

X_1 and X_2 are ethylene,

m is 2 to 50,

n is 0 to 50, and

p is 4 to 15.